



检 测 报 告

TEST REPORT

编号: SH151100225C01

报告日期: 2015/11/25

申请单位 : 嘉泰氟塑有限公司
Applicant JOINTEFLON COMPANY LIMITED
地 址 : 山东省青岛市九水东路 195 号
Address No.195, Jiushui East Rd, Qingdao Shandong China

以下测试样品由申请人提供及确认:

The following sample(s) was/were submitted and identified by/on behalf of the applicant as:

样品名称/Sample Name : 1# EXPANDED PTFE SHEET/膨胀聚四氟乙烯板
2# EXPANDED PTFE TAPE/膨胀聚四氟乙烯磁带
3# EXPANDED PTFE PACKING/膨胀聚四氟乙烯填料

接收日期/ Receiving Date : 2015/11/20

检测周期/Testing Period : 2015/11/20-2015/11/25

检测要求/Test Requested : 参见下一页/Please refer to next page(s)

检测方法/Test Method : 参考 FDA 21 CFR 175.300
With reference to FDA 21 CFR 175.300

检测结果/Test Results : 参见下一页/Please refer to next page(s)



批准 胡汉青
Approved by Salvia Hu

审核 刘世明
Reviewed by Leo Liu

编制 王一璐
Redact by Luciana Wang

第1页 共2页

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test report refer only to the sample(s) tested unless otherwise stated. This test report shall not be reproduced, except in full, without written approval of the Company. 本报告按本公司所制定之通用服务条款所编制发放。请注意本报告首页背面之此条款, 本公司之义务、免责、管辖权均有明确规定, 该条款也可向本公司索取。除非另有说明, 本报告仅对来样负责, 未经许可, 不得部分复制本报告。

优联(上海)检测有限公司

地址: 上海市外高桥保税区富特东三路76号32栋西3楼 200131
电话 (Tel): +86(0)21-68902737

United (Shanghai) Testing Services Co., Ltd.

3/F., Building 32, No. 76, Fute East 3 Road, Waigaoqiao Free Trade Zone, Shanghai, 200131
(Fax): +86(0)21-68392552

----- www.uts.com.cn -----



检测报告 TEST REPORT

编号: SH151100225C01

报告日期: 2015/11/25

检测结果/TEST RESULTS:

检测项目 Test Items		单位 Unit	检测结果 Test Results			要求 Requirements
			1#	2#	3#	
正庚烷萃取 / Total extractives in n-heptane	150° F, 2h	mg/in ²	<0.1	<0.1	<0.1	≤0.5 (single-use, volume is less than 3.78 L / 一次性, 体积小于3.78升) ≤1.8 (single-use, volume is more than 3.78 L / 一次性, 体积大于3.78升) ≤18 (repeated use / 重复使用)
蒸馏水萃取 / Total extractives in distilled water	212° F, 2h	mg/in ²	<0.1	<0.1	<0.1	
8%的酒精萃取 / Total extractives in 8% alcohol	212° F, 2h	mg/in ²	<0.1	<0.1	<0.1	

测试部位描述/TEST PART DESCRIPTION:

1# 白色塑料/White plastic

2# 白色塑料/White plastic

3# 白色塑料/White plastic

样品照片/SAMPLE PHOTO(S)



1#



2#



3#

.....报告结束/End of Report.....