

MTB-8000/7700 Crystal Epoxy Resin AB Glue TDS

MTB-8000/7700 hard crystal epoxy AB resin, made from the basic pure resin, defoamer, flow ping agent, thinner and additives by fine processing .Can be cured both with room temperature and by heating, forming automatic foam, automatic levelling, after curing, no bubble. With good diaphaneity, excellent surface gloss. The clearance can be five years with appropriate proportion.

APPLICATION

Especially for the epoxy coating of photos, photo album,Channel LED Letters,3D stickers,magnet,keyrings,crafts,namplates,mobile phone case and so on

Appearance &Character

Item(MTB-8000/7700)	Agent A	Agent B
Color	Transparent	Transparent
Viscosity	2680-2700	50-55
Mix Ration(by weight)	3	1
Hardness(shored)	38-42	38-42
Operation Time(25 Celsius degree)	35-40mins	
Curing Time (25 Celsius degree)	14-16h	
Curing Time(70 Celsius degree heating)	1.5h	
Curing Time (90 Celsius degree heating)	45mins	
Pressive Strength(kg/mm)	9.5	
Impact Strength(kg/mm)	8.8	
HDT(124 Celsius degree)	< 1%	



MTB-8000



MTB-7700