

GeofanTex GFS Range

Technical Data Sheet


GFT GeofanTex GFS Jan. 2018

GeofanTex GFS is 100% Polyester Staple Fiber Needle Punched non-woven Geotextile. The high quality PET raw material offers the most cost effective range of geotextiles bringing the maximum value to your project.

Manufactured from short fibres that are crimped, this range of geotextile offers excellent energy absorption characteristics as well as superior filtration performance. GeofanTex GFS is suitable in many applications, including the following:

- Underside protection of geomembranes / GCLs in containment systems
- Filtration
- Drainage and Separation

GeofanTex GFS is manufactured in widths of 6mts, thus reducing wastage by fewer overlaps and allows rapid, easy installation.



Mechanical Properties

(T: Typical value M: Minimum average roll value)

Properties (Standard)	Unit	GFS 100	GFS 150	GFS 200	GFS 250	GFS 300	GFS 350	GFS 400	GFS 450	GFS 500	GFS 600	
Tensile Strength	M	KN/m	3.6	4.5	7.5	10.0	13.0	14.0	16.4	18.0	20.0	28.0
[ASTM D 4595]	T		4.5	6.2	10.0	12.5	16.0	17.5	20.5	22.5	25.0	32.0
Tensile Elongation	M	%	50	50	50	50	50	50	50	50	50	50
[ASTM D 4595]												
Grab Strength	M	N	188	258	369	420	760	788	907	967	1045	1245
[ASTM D 4632]	T		260	326	594	696	875	920	1043	1128	1259	1610
Grab Elongation	M	%	50	50	50	50	50	50	50	50	50	50
[ASTM D 4632]												
Trapezoidal Tear	M	N	112	120	188	200	246	267	288	311	377	488
[ASTM D 4533]	T		130	145	209	250	315	357	360	414	441	629
CBR Burst Strength	M	KN(>=)	0.45	0.64	1.44	1.53	1.88	2.40	2.80	3.20	3.76	4.40
[ASTM D 6241]	T		0.65	0.74	1.60	1.96	2.25	3.00	3.50	3.96	4.70	5.50
Puncture resistance	M	N(>=)	184	276	368	460	552	644	656	828	920	1104
[ASTM D 4833]	T		230	345	460	575	690	805	820	1035	1150	1380

Hydraulic Properties

Flow Rate, 100mm head	L/s/m ²	161	142	106	85.5	75	61	53.2	50	48	44
[ASTM D 4491]											
Flow Rate, 50mm head	L/min/m ²	5600	4735	3251	2922	2659	2397	2113	2045	2013	1976
[ASTM D 4491]											
Permeability	(cm/s)	0.21	0.17	0.15	0.13	0.12	0.23	0.08	0.08	0.08	0.08
[ASTM D 4491]											
Apparent Opening Size O90	mm	0.089	0.079	0.061	0.061	0.062	0.074	0.061	0.059	0.057	0.059
[ASTM D 4751]											
Apparent Opening Size O95	mm	0.097	0.090	0.068	0.069	0.069	0.078	0.069	0.066	0.065	0.062
[ASTM D 4751]											

Physical Identification Properties

Thickness[ASTMD5199] (2KP)	mm	1.0	1.7	2.1	2.4	2.5	2.8	3.0	3.2	3.5	3.6
Roll Width	m(≤)	6	6	6	6	6	6	6	6	6	6
Roll Length	m(≥)	375	250	185	150	125	105	95	85	75	70
Approx Load Q'ty per 40' HQ	Sq. m	90000	60000	44400	36000	30000	25200	22800	20400	18000	16800

Above values are on an average basis, the data was obtained from in-house test laboratory, National test institutes and international test institutes. GFT keeps the right of data changes and the final explanation right. Liability Exclusion: This publication should not be construed as engineering advice. While information contained here is accurate to the best of our knowledge, GFT does not warrant its accuracy or completeness. The only warranty made by GFT for its products is set forth in our Product Test Report accompanies our shipment of the products, or such other written warranty as may be agreed by GFT and customer. GFT specifically disclaims all other warranties express or implied, including without agreed by GFT and customer. GFT specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade



Dalian GFT Geosynthetics CO.,LTD

NO. 10, Aixian Street , Gaoxin Dist., Dalian, China

TEL.:86-411-39569550 Fax: 86-4008266163-44899

Web:www.geofantex.com

Email:info@geofantex.com

GeofanTex GFS Range


Technical Data Sheet

GFT GeofanTex GFS Jan. 2018

GeofanTex GFS is 100% Polyester Staple Fiber Needle Punched non-woven Geotextile. The high quality PET raw material offers the most cost effective range of geotextiles bringing the maximum value to your project. Manufactured from short fibres that are crimped, this range of geotextile offers excellent energy absorption characteristics as well as superior filtration performance. GeofanTex GFS is suitable in many applications, including the following:

- Underside protection of geomembranes / GCLs in containment systems
- Filtration
- Drainage and Separation

GeofanTex GFS is manufactured in widths of 6mts, thus reducing wastage by fewer overlaps and allows rapid, easy installation.



Mechanical Properties

Properties (Standard)	Unit	GFS 800	GFS 1000	GFS 1200	GFS 1400	GFS 2000
Tensile Strength	M	40.0	55.0	59.0	65.0	91.0
[ASTM D 4595]	T	52.0	61.0	64.0	70.0	99.0
Tensile Elongation	M	50	50	50	50	50
[ASTM D 4595]						
Grab Strength	M	2019	3271	3351	3509	4513
[ASTM D 4632]	T	2731	3622	3812	4047	5279
Grab Elongation	M	50	50	50	50	50
[ASTM D 4632]						
Trapezoidal Tear	M	652	1155	1221	1325	1781
[ASTM D 4533]	T	998	1422	1531	1656	2254
CBR Burst Strength	M	5.95	8.92	9.44	10.76	14.15
[ASTM D 6241]	T	6.88	9.40	9.80	11.20	14.60

Hydraulic Properties

Flow Rate, 100mm head	L/s/m ²	79	61	44	36	30
[ASTM D 4491]						
Flow Rate, 50mm head	L/min/ m ²	2449	1710	1133	966	633
[ASTM D 4491]						
Permeability	(cm/s)	0.35	0.33	0.32	0.30	0.29
[ASTM D 4491]						
Apparent Opening Size O90	mm	0.089	0.079	0.061	0.061	0.062
[ASTM D 4751]						
Apparent Opening Size O95	mm	0.097	0.090	0.068	0.069	0.069
[ASTM D 4751]						

Physical Identification Properties

Thickness[ASTMD5199] (2KP)	mm	4.8	5.7	6.1	7.4	9.5
Roll Width	m(≤)	4	4	4	4	4
Roll Length	m(≥)	57	45	38	32	23
Approx Load Q'ty per 40' HQ	Sq. m	13680	10800	9120	7680	5520

Above values are on an average basis, the data was obtained from in-house test laboratory, National test institutes and international test institutes. GFT keeps the right of data changes and the final explanation right. Liability Exclusion: This publication should not be construed as engineering advice. While information contained here is accurate to the best of our knowledge, GFT does not warrant its accuracy or completeness. The only warranty made by GFT for its products is set forth in our Product Test Report accompanies our shipment of the products, or such other written warranty as may be agreed by GFT and customer. GFT specifically disclaims all other warranties express or implied, including without agreed by GFT and customer. GFT specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.



Dalian GFT Geosynthetics CO.,LTD

NO. 10, Aixian Street , Gaoxin Dist., Dalian, China

TEL.:86-411-39569550 Fax: 86-4008266163-44899

Web:www.geofantex.com

Email:info@geofantex.com