

Test Report

Report Number: 160309003SHF-BP-1

Applicant Name:	Guangzhou Goodsense Architectural Decoration Materials Co. Ltd	Report Date: 2016/3/28
Applicant Address:	No. 2, ZHUYUAN, WEST YANJIANG ROAD, TANBU TOWN, HUADU DISTRICT,	
Attn: Mr Shang		

Sample Description:

Product:	aluminum composite panel
Model:	/
Sample Quantity:	4 pcs
Sample ID:	S160309003SHF-001~004
Date Received:	2016/3/7
Date Test Conducted:	2016/3/9~2016/3/28

Tests Conducted:

As requested by the applicant, for details refer to attached pages(s).

Conclusion:

For details refer to attached page(s).
The conclusions of this test report may not be used as part of the requirements for Intertek product certification. Authority to Mark must be issued for a product to become certified.


Test Items, Method and Results:

Test item	Test method	Test result	
Serviceability Testing	ICC-ES AC 25 "Acceptance Criteria for Metal Composite Material (MCM)", approved October 2010.	Positive	0.75 kN/m ²
		Negative	1.00 kN/m ²

Note:

1. The panel was fastened by screws to the wood frame. The screws were spaced 300mm from each other.
2. The type of the screw was #10x1¹/₂"-Tek3, see photo below.
3. The usage span of the panel was 1200mm. The result was based on the deflection limit of 1/60 of the span.

Test photo:Screw type #10x1¹/₂"-Tek3



Test set up

Appendix A: Sample received photo



Approved by:

Sun Sun

Name: Sun Sun
Title: Approver

Jodie Zhou

Name: Jodie Zhou
Title: Reviewer

Sally Xie

Name: Sally Xie
Title: Project Engineer

The End of Report

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.