

DQ 301

Quick Drying Adhesive

DESCRIPTION:

- Easy to use
- Good temperature resistance
- High strength, impact resistance



APPLICAION:

Used to bond one or more tooling board together, easy to use, with reliable bonding and matching processing characteristics.

PARAMETER:

Туре	Color	Viscosity (CPS) (25℃)	Mix ratio	Pot life (25℃)	Cure Time (25℃)	Shelf life (25℃)
Quick drying adhesive	Adhesive A: translucent	A: 4000-6000	100	5mins	24 Hours	6 Months
	Adhesive B: translucent	B: 4000-6000	100			

Remarks: The above parameters are slightly different due to factors such as different materials, surface cleanliness, temperature difference and other factors. The data is for reference only.

Temperature resistance:-60~110°C



DQ 301

Quick Drying Adhesive

USAGE METHOD:

- The bonding site should be kept clean, dry and flat.
- When using, adhesive A and, adhesive B are applied to the two tooling board, respectively. Then connect the two tooling board together and move the two tooling board slightly to the left and right to mix the adhesive.

PRECAUTIONS:

- Keep the workplace ventilated.
- Wear gloves when using. If you touch your skin or eyes, rinse immediately with water or seek medical attention.
 - Do not mix adhesive A and B when not in use.
- Store in a cool, dry, ventilated place away from high temperatures.
 - When using in batches, please test first.

PACKAGING:

Quick drying adhasiya	Adhesive A	1KG
Quick drying adhesive	Adhesive B	1KG

Dongguan Dongquan Mould Materials Co., Ltd.

TEL:(+86)0769-8587 8968 Web:www.dqtoolingboard.com

Mobile:+86 13265122244 Email:info@dqtoolingboard.com