

DESCRIPTION:

- Curing at room temperature
- Short curing time
- Color are matched to the relevant board



APPLICATION:

- Suitable for repairing the polyurethane tooling board

PARAMETER:

Type	Color	Density (g/cm ³)	Mix ratio	Pot life (25°C)	Light Handling Time (25°C)	Shelf Life (25°C)
Repair Material	A(resin): Customized colors	customize	4	5mins	2 Hours	1 year
	B(hardener): Light yellow	customize	1			

Remarks: The above parameters are slightly different due to factors such as different materials, surface cleanliness, temperature difference and other factors. The data is for reference only.

USAGE METHOD:

- Mix the two materials thoroughly in a ratio of 4:1, and fill the mixed materials into the place to be repaired.
- Repair material A and B can be used immediately after mixing.



DQ 401

Repair Material

PRECAUTIONS:

- Keep the workplace ventilated.
- Wear gloves when using. If you touch your skin or eyes, rinse immediately with water or seek medical attention.
- Do not mix repair material A and B when not in use.
- Store in a cool, dry, ventilated place away from high temperatures.
- When using in batches, please test first.

PACKAGING:

Repair Material	A:resin	500G
	B:hardener	125G

Dongguan Dongquan Mould Materials Co., Ltd.

TEL:(+86)0769-8587 8968

Web:www.dqtoolingboard.com

Mobile:+86 13265122244

Email:info@dqtoolingboard.com