

### DESCRIPTION:

- Quick to process
- Fine cell structure
- Homogeneous surface
- Easy to process by hand



### APPLICATION:

- Design study
- Master model
- Styling models
- Data models

### PARAMETER:

Type	DQ500
Color	Brown
Density(ISO 1183)	0.5g/cm <sup>3</sup> or 31 lb./ft. <sup>3</sup>
Hardness(ISO 868)	52-57shore D
Coefficient of thermal expansion(ISO 11359)	50-55 x 10 <sup>-6</sup> K <sup>-1</sup>
Hot deformation temperature(ISO 75)	65-70°C
Flexural strength(ISO 178)	10-15 MPa
Compressive strength(ISO 604)	10-15 MPa
Tensile strength	-
Specifications	1490x500x(50/75/100/150)mm Other dimensions on request

### STORAGE:

- ★ The material should be stored flat and in a dry place avoiding large temperature variations.

**Dongguan Dongquan Mould Materials Co., Ltd.**

TEL:(+86) 0769-8587 8968

Mobile:+86 13265122244

Web:www.dqtoolingboard.com

Email:info@dqtoolingboard.com