

DESCRIPTION:

- Easy to machine
- Less dust during processing
- Excellent surface structure
- Good compressive strength



APPLICATION:

- Automotive die models
- Master model
- Styling prototypes
- Vacuum forming mould

PARAMETER:

Type	DQ650
Color	Brown
Density(ISO 1183)	0.65g/cm ³ or 40 lb./ft. ³
Hardness(ISO 868)	65-68shore D
Coefficient of thermal expansion(ISO 11359)	50-55 x 10 ⁻⁶ K ⁻¹
Hot deformation temperature(ISO 75)	75-80°C
Flexural strength(ISO 178)	30-35 MPa
Compressive strength(ISO 604)	45-50 MPa
Tensile strength	20-25 MPa
Specifications	750x500x(30/35/50/75/100)mm 1500x500x(50/75/100/150/200)mm Other dimensions on request

STORAGE:

- ★ The material should be stored flat and in a dry place avoiding large temperature variations.

Dongguan Dongquan Mould Materials Co., Ltd.

TEL:(+86) 0769-8587 8968
Mobile:+86 13265122244

Web:www.dqtoolingboard.com
Email:info@dqtoolingboard.com