

LY POWDER



LAP100.29Mo1



APPLICATION




LAP100.29Mo1 is widely used for the production of Sintered PM parts require high heat treatment performance.

SPECIFICATION

Chemical Properties (%)	Unit	Specification	
		Min	Max
C	%		0.01
Si	%		0.05
Mn	%		0.15
P	%		0.02
S	%		0.015
Mo	%	0.50	0.70

Physical Properties			
Apparent density	g/cm ³	2.90	3.15
Flow rate	s/50g		28
Green density 600Mpa	g/cm ³	7.00	

Particle size distribution (%)			
180-212um	%		1
150-180um	%		10
45-150um	%		
-45um	%	10	30



PROPERTIES

LAP100.29Mo1 + 0.5%C + 0.8%Zn-st, conditions: temperature 1120°C; Sintering time 30min; Sintering density 7.0(g/m³); Rockwell hardness(HRB) 78; Tensity strength(MPa) 410; Elongation(%) 1.95; Impact energy(J) 21.