## Anthracite based carbon additive (CAC)

It is made from well-selected Ningxia Taixi anthracite .

Spe Grad	F.C( %)	Ash( %)	Moisture( %)	V.M( %)	S	N	Size
SuperGra de	95min	4.0max	0.5max	1.0max	0.25m ax	0.3m ax	As client's dema
1st Grade	94min	4.5max	0.5max	1.0max	0.3ma x	0.3m ax	nd
2stGrade	93min	6max	1.5max	1.5max	0.35m ax	0.4m ax	
3stGrade	92min	6.5max	1.5max	1.5max	0.35m ax	0.4m ax	
4stGrade	90min	8.5max	1.5max	1.5max	0.35m ax	0.4m ax	
5stGrade	85min	13max	3max	1.5max	0.4ma x	0.4m ax	
6stGrade	80min	16max	3max	1.5max	0.4ma x	0.4m ax	
Packing	As client	's demand					

## **Calcined petroleum coke(CPC)**

It is calcined in the 1350°C calcined kiln in rank type to obtain the lower volatile highest grade.

Spec Grade	F.C(% )	V.M(% )	Moisture( %)	S(%)	Ash(% )	N(ppm)	Siz e
CPC	98min	0.7max	0.5max	0.7ma x	0.5max	10000ma x	*
CPC	98min	0.7max	0.5max	0.5ma x	0.5max	10000ma x	
CPC	98min	0.7max	0.5max	0.1ma x	0.5max	10000ma x	
Packin g	As clients	s' demands					

## **Graphitized Petroleum Coke(GPC)**

It is made from low sulfur and low nitrogen petroleum coke by  $2500-3500^{\circ}\text{C}$  temperature graphite annealing.

Spe Grad e	F.C( %)	Ash( %)	Moisture( %)	V.M( %)	S(%)	N(%)	Size(m m)
Gpc	98.5mi n	0.5max	0.5max	0.5max	0.05m ax	300m ax	*
Packin g	As clients' demand						